

DOCRIL N

MARINE

Roll lenght:	60 m	(65,6 yards)
Application:	Marine, Sun Protection	

PROPERTIES



Composition:	100% Solution Dyed Acrylic	
Width:	153 cm	(60")
Weight:	335 g/m ²	(9,88 oz/yd ²) UNE 40339
Water penetration resistance:	≥ 105 cm H ₂ O	(≥0,40" H ₂ O) UNE EN ISO 811
Resistance to surface wetting - Spray Test:	100 note (max. 100)	UNE-EN ISO 4920
Oil Repellency:	≥ 5	AATCC 118
Warp/Weft tensile strength:	140/90 daN/5 cm	(314/202 lbf/2 in.) UNE-EN ISO 13934-1
Warp/Weft elongation at break:	≤ 25/≤ 25 daN	UNE-EN ISO 13934-1
Warp/Weft tear strength:	5/3 daN	(11,3/6,8 lbf/2 in.) UNE-EN ISO 13937-2
Colour fastness to artifical light:	≥ 7 note blue scale (max. 8)	UNE-EN ISO 105-B02
Colour fastness to artifical weathering:	≥ 7 note blue scale (max. 8)	UNE-EN ISO 105-B04
Colour fastness to seawater:	5 note (max. 5)	UNE-EN ISO 105-E02
Colour fastness to chlorinated water (from pools):	5 note (max. 5)	UNE-EN ISO 105-E03

Tolerance +/- 5% average values. Non-contractual information. The data are result of tests performed in our laboratories.
For more technical information, please contact us at info@citel.com

CARE&CLEAN



Maintenance instructions: Remove dust with a vacuum cleaner, without rubbing.
Clean with a sponge or a soft brush dampened with water and soap.
When used in awnings, it is very important to allow the fabric to dry completely before roll it up

WARRANTY

5 years

Made in Europe